

CHEMSTUK



POLY COVER 233 | POLYURETHANE TOP COAT

Chemstuk Pty Ltd

Product Description

Two-component acrylic polyurethane topcoat designed to provide excellent gloss and colour retention, UV resistance and long-term protection in severe environments.

Recommended Uses

- Topcoat for epoxy systems
- Structural steel
- Industrial and marine environments
- Exterior protective coatings

Technical Data

Finish: Semi-Gloss / Semi-Flat

Colour: White / Custom

Solids: 55 ±2%

Coverage: ~13–14 m²/L @ 40 microns

Flash Point: ~32°C

Specific Gravity: ~1.3 kg/L

VOC: <380 g/L

Mixing

Mix Ratio (A:B): 10 : 1

Pot Life: ~5 hours @ 20°C

Application

Apply by airless spray or brush. Thin up to 10–30% depending on method.

Drying Times (20°C)

Touch Dry: ~4 hours

Hard Dry: ~24 hours

Full Cure: ~7 days

Surface Preparation

Apply over properly prepared and primed surfaces such as epoxy midcoat or primer.

DISCLAIMER

This Technical Data Sheet is to be used as a guide only; it is NOT a specification. Chemstuk Pty Ltd has no control over the use or storage of this product and therefore does not accept liability in this regard. Any verbal advice given should not be regarded as authoritative information. This information is subject to change without notice; all applicators should ensure they have current information. This product is intended for the use only of skilled tradesmen and, where applicable, statutorily licensed tradesmen experienced and trained in the use of this product. Due to differences in substrates, application methods and local conditions, purchasers of these products must ensure that they are suitable for their specific application before using these products. While the information contained in the TDS and SDS is accurate to the best of our knowledge, Chemstuk Pty Ltd cannot guarantee that the information contained is wholly comprehensive. Subject to the provisions of the Trade Practices Act, the company's liability in relation to defective products shall be limited to replacement of the product if the product is proven to be defective.